

Article-No.:

Model Name:

506997

askö Fire Action Top Knitted Welt

KP

Design & Construction:

Description: The models of the FIRE ACTION range stand out due to their wide variety and very broad field of application. In accordance with the latest certification EN 659:2008 (EN 659+A1+AC:2009). Perfect fit within the sizes and high degree of finger dexterity. High degree of wearing comfort with a firm grip and good protection against mechanical risks. Extremely hard-wearing membrane with all model of the FIRE ACTION range. All models are heat and cold insulating.



© by askö GmbH

Sizes: 7 - 12
Color: 1999 black

Materials:

inside hand, knuckle protection & backhand: Elastic knitted material made of 100% Kevlar® with flame-retardant silicone-carbon coating
Knitted welt: 100% Kevlar® knitted material
Insulation, lining: Interlock knitted fabric made of 100% Kevlar® directly needled with 50% Kevlar® non-woven fabric and 50% NOMEX, knitted material F 1320 NF/FC patented by askö
Insert: Porelle membrane PTFE, waterproof, windproof with optimum breathability, anatomical
Applications: Half-rings on right and left glove and snap hooks, padding at ball of hand
Length: Approx. 30 cm long

Product instructions:



For drying hang up on the fingertips.

Cleaning:

Recommendation: The use of commercially available cleaning agents (e.g. brushes, cleaning cloths etc.) is recommended. The gloves should be checked to ensure they are intact before being used again.

Restriction: Washing or dry-cleaning should only be carried out after consulting an accredited firm of specialists. For changes to the properties the manufacturer is not able to accept any liability here.

Pictograms and power levels according DIN EN 659:2008 (EN 659+A1+AC:2009) CAT III

Parameter	Requirement	Result	Level
Abraison (EN 388)	min. 3	2000 Cycles	3
Cut resistance (EN 388)	min. 2	30,9 Index	5
Tear resistance (EN 388)	min. 3	112 Newton	4
Puncture resistance (EN 388)	min. 3	105 Newton	3
Burning behavior (EN 407)	4	Burning time Glowing time =0	4
Dexterity (EN 420)	min. 1	Test pen 6,5 mm	4
Convective heat resistance (EN 367)	HTI ₂₄ ≥13	Back 34 Palm 28	-
Radiant heat resistance (EN ISO 6942)	RHTI ₂₄ ≥20	Mean value 36	-
Contact heat resistance (EN 702)	t _c ≥10s	Dry 16 Wet 15	-
Seam breaking strength (ISO 13935-2)	Min. 350 N	362 N	-



Performance data EN 388 – mechanical risks

Testing	Level 1	Level 2	Level 3	Level 4	Level 5
1.number :Abraison (Cycles)	100	500	2000	8000	
2.number:Cut resistance (Index)	1,2	2,5	5,0	10,0	20,0
3.number:Tear resistance (Newton)	10	25	50	75	
4.number:Puncture resistance (Newton)	20	60	100	150	

Testing: 0197 - TÜV Rheinland LGA Products GmbH - Tillystraße 2 - D-90431 Nürnberg

Contact: askö GmbH - Innovative Schutzausrüstung
Adolph-Kolping-Str. 6 , D - 72393 Burladingen
Tel.: 07475 / 95000 - 0 Fax: 07475 / 95000 - 29
eMail: info@askoe-online.de Website: www.askoe-online.de